

TECHNICAL DATA SHEET
PRODUCT:"BULLDOG" B-SEAL REGULAR
EPOXY COMPOUND



PRODUCT DESCRIPTION

"Bulldog B-Seal"- Regular, is an Epoxy Putty, consisting of a Resin component and a Hardner component in cake form,packed in separate pouches. It is a slightly slow setting putty ,but yields very good bond strength on setting and has very good resistance to water and also good resistance to alkalis, acids solvents etc. A universal sealing,fitting and repair compound.

COMPOSITION

A mixture of Epoxy Resin and Epoxy Hardner with various mineral powders and additives.

APPLICATION AREAS

Seals leakages in tanks,vessels, cisterns, pipes etc.Repairs worn out shafts, cracked machine parts,fills gaps in body parts,sheet metal fabrication, etc.

DIRECTIONS FOR USE

- 1.Cut eual quantities of Resin & Hardener.
- 2.Cut only required quantity.
- 3.Mix thoroughly to form a homogeneous paste.
- 4.IMP: Make surface to be sealed completely dry and free of oil / grease etc.
- 5.Make the surface slightly rough with a file,sand paper etc.for best results.
- 6.Apply Bulldog B-Seal mixed putty where required and press lightly.
- 7.After 20 minutes give shape with a damp cloth.
8. Sets in 90 minutes (at 28 C) to form to leak a proof seal.

CLEANUP

Clean up with Acetone and Toulene.

DISCLAIMER

The information contained herein is given in good faith , based on our tests & knowdege of the product; as a guide . The responsibility is of the user to verify its usability for any application. The company ,The Standard Products Mfg. Co. Mumbai , disclaims all warranties expressed or implied and takes no responsibilities for any loss or damage arising from the use of its products.

For further information please contact:

The Standard Products Mfg. Co.

2/14, Marol Co-op. Indl. Estate, Makawana Road,
 Marol, Andheri (E), Mumbai – 400 059.
 Customer Support : 2850 0970 / 2859 0668
 E-mail :spmc59@gmail.com

**PROPERTIES OF COMPONENTS
 (BEFORE MIXING)**

Appearance - Resin : Light green colour putty
 - Hardner : Black colour putty

Density -Resin : 2.10 - 2.20 g/ml
 -Hardner : 2.00 - 2.10 g/ml

MIX PROPERTIES

Mixing ratio : Resin to Hardener

By Weight : 100 : 100
 By Volume : 100 : 100

Pot life : 45 minutes

Setting time : 90 minutes

Fully cured : 12 hours
 (Full Strength)

SAFETY INSTRUCTION

- 1.Keep away from children.
- 2.Avoid excessive contact with body. Clean with plenty of water in case of eye contact.
- 3.Cannot be ingested. Lethal if ingested.
- 4.Do not induce vomitting,in case of ingestion. Consult a physician immediately.
- 5.Do not inhale or used in closed spaces.